

EASY-GRIP BLACK



Anti-slip overshoe



- Composition: 100% rubber.
- Professional use: For greasy, wet and slipping surfaces.
- ✓ Outstanding grip coefficient
- ✓ Stretch fit structure : 4 Sizes from 34 to 50
- ✓ Color-coded sizes : identify the size at a single glance
- ✓ Can be adapted to most kind of footwear
- ✓ Hygienic and comfortable solution
- ✓ Reusable and waterproof
- ✓ Tiger-grip® antislip sole with self cleaning studs

REF « EGN »

Certifications

EUROPEAN DIRECTIVE :
89/686/CE

(personal protective equipment)



EUROPEAN STANDARDS

CE certification :

0075/1344/161/07/13/0626

- NF EN ISO 20347 /2012
- NF EN 13287
- Oil resistance (FO)

CE PPE CERTIFIED Risk II

Certified organism:

CTC N° 0075/69367 Lyon - France



AMERICAN STANDARDS

- ASTM F 2913



CANADIAN STANDARDS

- Acceptance EN ISO 13287 (SRC)

• NF EN 13287 – Antislip properties

Certification SRC = SRA + SRB

SRB : Anti-slip coefficient on steel floors with glycerin

SRA : Anti-slip coefficient on ceramic floors with detergent

Surface	Contact with	Standard ISO 13287	EASY-GRIP results
Steel	Oil	SRB = 0.18	+ 340% = 0.62
	Detergent	SRA = 0.32	+140% = 0.54
Ceramic	Water	-	0.62

Up to

Physico-mechanical test

Test	Hardness	Abrasion resistance	Density	Breaking traction resistance	Breaking extension	Tearing resistance
Standard		ISO 4649/2002	ISO 4649/2002	EN 12803	EN 12803	ISO 34-1-Méth. A
Unit	Shore A	Mm ³	g/cm ³	daN/cm ²	%	daN/cm
EASY-GRIP results	50	140	1,16	137	603	10,5

Antistatism: The overshoe meets antistatic properties.

The shoe and overshoe combination must necessarily be tested by the user

Sizes



	S				M				L				XL			
EU Sizes	34	35	36	37	38	39	40	41	42	43	44	45	46	47	48	+
UK Sizes	1	2	3	4	5	6	6,5	7	8	9	10	10,5	11	12	13	+
US Woman	4	5	6	7	7,5	8	8,5	9,5	10	11						
US Man					5,5	6	7	8	8,5	9,5	10	11	11,5	12,5	13	+

For a proper use of the overshoes, it is important to ensure that the overshoes fit neatly over the user's footwear

Storage and maintenance



- Hand, machine and autoclave washable - Let them dry naturally
- Store in a dry place, away from temperature variation
- Do not use below a temperature of -20°C.
- Autoclave sterilization