

TUV NORD (M) Sdn. Bhd. (288858-P)*(formerly known as RWTUV (M) Sdn. Bhd.)*

No, 20, Jalan Tiara 3, Tiara Square,
Taman Perindustrian UEP,
47600 Subang Jaya,
Selangor, Malaysia



Tel: +6-03-8023 2124

Fax: +6-03-8023 4410

Email: malaysia@tuv-nord.com

Internet: www.tuv-nord.com

Report No.

TUVNORD – 085-07-11-2

Contact

Chong Kar Yee

Email: kychong@tuv-nord.com

Direct Dial

Tel.: 03 - 80232124

Fax: 03 - 80234410

Date

July 14th, 2011

Customer	SAFETYWARE SDN BHD
Customer Address	Plot 237, Lengkok Perindustrian Bukit Minyak 3, Bukit Minyak Industrial Estate, 14100 Simpang Ampat, Penang, Malaysia.
Sample Description	Unlined Natural Rubber Glove
Brand	Safetyware
Model	FoodPlus AU1712
Date of Sample Received	7 th July 2011
Date of Analysis	7 th July 2011 – 14 th July 2011

TEST RESULTS

No.	Test Description	Test Result
1	Overall migration for glove sample according to FDA 21 CFR Part 177.2600 - Rubber articles intended for repeated use.	As Reported

Name: Chong Kar Yee	Name: Lim Sai Seong
Date: 14/07/2011	Date: 14/07/2011

This report is CONFIDENTIAL and is the customer property as mentioned above. TUV NORD (M) Sdn. Bhd. shall not be responsible for any distribution copies of this report or any implications arise from such distribution.



Objective

To perform overall migration for glove sample according to FDA 21 CFR Part 177.2600-Rubber articles intended for repeated use.

Test Procedure as per 21 CFR 177.2600

Glove sample was extracted at below specific condition:

- a) Distilled water at reflux temperature for 7 hours
- b) n-Hexane at reflux temperature for 7 hours

The extract was then evaporated to dryness and the overall migration was then measured using an analytical balance.

Analysis Result

Extraction Conditions	Overall Migration for Glove Sample (mg/in ²)	Requirement as per 21 CFR Part 177.2600 (mg/in ²)	Inferred Result
Distilled water at reflux temperature for 7 hours	1.6	Not exceed 20	Complied
n-Hexane at reflux temperature for 7 hours	1.8	Not exceed 175	Complied