

Sponsor:
Wong Kee Wei
Safetyware Sdn. Bhd.
Plot 237, Lengkok Perindustrian Bukit Minyak 3
Bukit Minyak Industrial Estate
Simpang Ampat, Pulau Pinang, 14100
MALAYSIA

Bacterial Filtration Efficiency (BFE) Final Report

Test Article: 1302

Study Number: 1334005-S01 Study Received Date: 21 Aug 2020

Testing Facility: Nelson Laboratories, LLC

6280 S. Redwood Rd.

Salt Lake City, UT 84123 U.S.A.

Test Procedure(s): Standard Test Protocol (STP) Number: STP0004 Rev 18

Deviation(s): None

Summary: The BFE test is performed to determine the filtration efficiency of test articles by comparing the bacterial control counts upstream of the test article to the bacterial counts downstream. A suspension of *Staphylococcus aureus* was aerosolized using a nebulizer and delivered to the test article at a constant flow rate and fixed air pressure. The challenge delivery was maintained at $1.7 - 3.0 \times 10^3$ colony forming units (CFU) with a mean particle size (MPS) of $3.0 \pm 0.3 \, \mu m$. The aerosols were drawn through a six-stage, viable particle, Andersen sampler for collection. This test method complies with ASTM F2101-19 and EN 14683:2019, Annex B.

All test method acceptance criteria were met. Testing was performed in compliance with US FDA good manufacturing practice (GMP) regulations 21 CFR Parts 210, 211 and 820.

Test Side: Inside

BFE Test Area: ~40 cm²

BFE Flow Rate: 28.3 Liters per minute (L/min)

Conditioning Parameters: 85 ± 5% relative humidity (RH) and 21 ± 5°C for a minimum of 4 hours

Test Article Dimensions: ~172 mm x ~165 mm

Positive Control Average: 2.5 x 10³ CFU
Negative Monitor Count: <1 CFU

MPS: 3.0 μm





Christopher Acker electronically approved for

James Luskin

19 Sep 2020 04:41 (+00:00)

Study Completion Date and Time

801-290-7500

Study Director

nelsonlabs.com

sales@nelsonlabs.com

FRT0004-0001 Rev 22



Results:

Test Article Number	Percent BFE (%)
1	99.8
2	99.8
3	99.5
4	99.8
5	99.5

The filtration efficiency percentages were calculated using the following equation:

$$\% BFE = \frac{C - T}{C} \times 100$$

C = Positive control average

T = Plate count total recovered downstream of the test article Note: The plate count total is available upon request

